Durostone® CFR767

Permali Composites S.A.S., introduces a high performance composite for use in harsh environments such as fluxes containing halides or dicarboxylic acids. Durostone ®CFR767 has been specifically developed to solve the issues of surface degradation caused by aggressive fluxes.

TECHNICAL DATA	
Grade	Anti-Static
Colour	Brown
Density (g/cm³)	1.80
Flexural Strength @ 23°C – 3 point support ⊥ (Mpa)	380
Flexural Strength @ 150°C - 3 point support ⊥ (Mpa)	260
Flexural Strength @ 185°C - 3 point support ⊥ (Mpa)	150
Modulus of Elasticity @ 23°C (Mpa)	18.000
Modulus of Elasticity @ 150°C (Mpa	14.000
Modulus of Elasticity @ 185°C (Mpa	10.000
Water Absorbtion (%)	<0.20
Coefficient of Linear Expansion (10 ⁻⁶ /K) Between 30°C & 200°C	11
Thermal Conductivity (W/m°K)	0.23
Maximum Operating Temperature (°C), 10 – 20 seconds	380
Standard Operating Temperature (°C)	300
Surface Resistivity (ohms)	10 ⁵ – 10 ⁹
Chemical Resistance *	Excellent

• Chemical Resistance test carried out on wave solder machine using an ORH1 flux which contains the halide, hydro-bromic acid.

Sheet Size (mm)	2440 x 1220
Thickness' available	5mm, 6mm, 8mm, 10mm, 12mm
Thickness Tolerance	± 0.20mm
Flatness Tolerance (for a panel size of 300mmx300mm)	0.20mm
Parallelism	0.10mm